

Measurement Test Report

Customer:	Finike	Insaat	Ve	Ticaret,	LTD.	
-----------	--------	--------	----	----------	------	--

Contact: Selcuk Baysari

P.O. #:

EFT

Job #:

M-042

Measurement Date: Report Date: 8/1/2012 8/1/2012

Optical Properties

Full scale = 1.000

Sample	Solar Ref at Air M		Thermal Emittance at 300K		
	0.737	0.744	0.870	0.863	
NOTION NAME OF THE	0.735		0.870		
Finike Marble	0.762		0.869		
Lymra Limestone	0.743		0.873		
	0.746		0.880		
	0.741		0.857		

Solar Reflectance Index (SRI)

	Convection Coefficient				
Sample	Low, 5 W/m²K	Medium, 12 W/m²K	High, 30 W/m²K		
Finike Marble Lymra Limestone	90.6	91.0	91.4		

SRI Calculation per ASTM E1980, Approach II

Bryan C. Kiep

Bryan C. Kiep

Philip A. Mathis

helig a Matthis

Solar Absorptance

These measurements were made in accordance with ASTM standard test method E903, Solar Absorptance, Reflectance, and Transmittance of Materials Using Integrating Spheres.

Measurement statistics

Uncertainty: ± 0.03 of a full-scale value of 1.0

Repeatability: ± 0.005 of a full-scale value of 1.0

Instrument Identification

Model: LPSR 200IR (S/N 108)

Sphere geometry: "Absolute" integrating sphere, 15°/h

Manufacturer: AZ Technology, Inc.

Instrument Calibration:

LPSR: February, 2011

Computation of Solar Properties

The solar spectral irradiance distribution and the weighting method used for the computation of the solar optical property are in compliance with the standard as called out in paragraphs of section 8.3 of ASTM E903.

Emittance

These measurements were made in accordance with AZ Technology test methods for near-normal emittance and total hemispherical emittance at 300K. Near normal emittance measurements are traceable to E408 through round robin testing with the Gier Dunkel DB-100.

Measurement statistics

Uncertainty: ± 0.01 of a full-scale value of 1.0 (gray bodies)

±0.03 of a full-scale value of 1.0 (nongray bodies)

Repeatability: ± 0.005 of a full-scale value of 1.0

Instrument Identification

Model: TESA 2000 (S/N 1106-115)

Collector geometry: "Absolute" ellipsoidal cavity, 15°/h

Manufacturer: AZ Technology, Inc.

Calibration Puck Identification

Model: Hemispheric Emittance Calibration Puck

(S/N 099928-001)

Manufacturer: AZ Technology, Inc.

Instrument Calibration

Spectrafire: Prior to each usage.